

Chemical Compositions (wt%)													
Material	C	Si	Mn	P	S	Cu	Ni	Cr	Mo	Al	V	Ti	Fe
FC300	2.99	2.00	0.74	0.020	0.015	0.77							
Ti-6Al-4V	0.008									6.32	4.42	Bal	0.21
SUS316	0.02	0.47	0.95	0.024	0.001		10.04	16.50	2.1				
SUS403	0.13	0.44	0.40	0.024	0.024		0.26	11.57					
SUS430	0.005	0.47	0.12	0.026	0.001		0.10	16.42					