

T.P. No.	Test Temp. (°C)	D0 (mm)	D (mm)	L0 (mm)	L (mm)	0.2% offset Y.S (N/mm ²)	Tensile Strength (N/mm ²)	Elongation (%)	Reduction of Area (%)	Fracture Location
Spec. (JIS G 5501)							≥ 300			
1		6.01	6.00	30.02	30.24	251	287	0.7	0.3	B
2	RT	6.01	6.00	30.01	30.25	244	287	0.8	0.3	B
3		6.01	6.00	30.01	30.27	249	292	0.9	0.3	B